

Durex® Air Stop

Flexible Latex Copolymer Air Barrier & Waterproofing Membrane

- Description** Durex® Air Stop is a single-component, liquid-applied, water-based copolymer rubber air barrier and waterproofing membrane. Applied by roller, trowel or spray equipment, it cures to form a tough, seamless, elastomeric membrane which is resistant to air leakage and water ingress under hydrostatic pressure. In its liquid state, Durex® Air Stop is light blue in colour and cures to a translucent dark-blue colour.
- Uses** Durex® Air Stop is used as an air barrier within the building envelope and as a seamless waterproofing membrane. It may be applied to most common surfaces and integrated into various wall systems in both new construction and restoration. Durex® Air Stop is a Class III Air Barrier and a water penetration barrier at a maximum wet or dry film thickness of 0.39 mm. Typical uses are:
- Water penetration/air barrier for EIFS application
 - New and existing foundation walls
 - Plywood, cement board and exterior-grade gypsum board sheathing
 - Exterior walls of mechanical and electrical rooms
 - Split slab waterproofing
 - ICF - Insulated Concrete Forms
- Features**
- Highly flexible, bridges cracks up to 1/16" which may form in the substrate
 - Liquid application assures a monolithic, seamless membrane
 - Water-resistive (WRB) air/vapour-barrier membrane. Prevents air leakage and water ingress through porous building materials.
 - Remains firmly bonded to the substrate even when applied over damp surfaces
 - Water-based technology allows for simple and safe application and easy clean up
 - Can be sprayed
 - Excellent for waterproofing foundation walls constructed with ICF (Insulated Concrete Forms)
 - Results in a paintable finish

TECHNICAL DATA

PHYSICAL PROPERTIES		
Product Type	Water-based copolymer	
Appearance	Light-blue viscous material in its liquid state	
Specific Gravity	0.98	
ph Level	6.0	
Vapour Pressure	(mmHg) 17 @ 20°C	
Boiling Point	Approx. 100°C	
Application Temperature	Above 5°C (40°F)	
Coverage	25-28 m ² (250-300ft ²) per 18.9L (5 gal) pail at 1mm (40 mil) wet film thickness or at 0.05mm (20 mil) dry film thickness	

PERFORMANCE PROPERTIES	METHOD	RESULT
Bond Strength	ASTM D321	0.51 MPa (73.3 psi)
Tensile Strength	ASTM D412	2.73 MPa (390 psi)
Elongation	ASTM D412	340%
Plastic Flow		No sagging at 60°C for 5 hours
Air Leakage	ASTM E283-91 (1999) (NRC Classification)	0.0001L/(s.m ²) Type III Air Barrier
Water Vapour Permeance	ASTM E96	48 ng/Pa.s.m ² @ 1mm (wet), 0.39 mm (dry)

* When Durex® Air Stop is intended to be used as an air barrier, the application thickness should not exceed 1.0 mm WET (0.39 mm DRY).

Storage	Store Durex® Air Stop containers tightly sealed and store stacked off the ground with ambient temperatures above 2°C (35°F). KEEP FROM FREEZING. DISCARD ALL FROZEN MATERIALS.
Application	Substrate must be dry, clean, sound and free of weak and powdery surfaces, dust, dirt, oil, grease and other deleterious materials which may be detrimental to Durex® Air Stop during or after curing. (Consult Durabond Products Limited for questionable substrates). Durex® Air Stop may be applied by roller, trowel or spray. For spray application, use a conventional airless unit with a 0.025 tip and a minimum of 3,000 psi.
Limitations	Durex® Air Stop is not recommended for use: <ul style="list-style-type: none"> . When ambient, surface and material temperatures are below 2°C (35°F) during application and curing period . As a permanently exposed membrane
Curing/Drying Time	Allow material to dry at air and surface temperature of 2°C (35°F) or higher. Curing time will differ depending on specific application conditions. Relative humidity, temperature and airflow will effect curing time. Average conditions and standard thickness will achieve tack-free film in 1 to 3 hours and full cure within 7 days. DO NOT SUBSTITUTE OR COMPENSATE DUREX® AIR STOP WITH WATER OR OTHER ADDITIVES.
Clean-up	Durex® Air Stop is a water-based emulsion and does not require the use of solvents for cleaning up. Use light soap and water to clean uncured material. Cured material is best removed with xylol or by mechanical means.
Health and Safety	For information and advice on the safe handling, storage and disposal of chemical products, refer to the most recent MSDS sheet containing physical, environmental, toxic and other safety/materials handling data. For industrial use only. Keep out of reach of children.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Products Ltd. sales representative.

DURabond

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01