

Durex® Uraflex 362

High Abrasion-Resistant Elastomeric Polyurethane Traffic-Bearing Topcoat

- Description** Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat is a two-component, solvent-free, high solids elastomeric polyurethane topcoat specially formulated for high-level traffic-bearing surfaces. It is designed to adhere to Durex® Uraflex 360 Elastomeric Polyurethane Waterproofing Membrane and Durex® Uraflex 361 Traffic-Bearing Topcoat and other similar traffic-bearing coatings to form a highly effective traffic-bearing waterproofing system.
- Uses** Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat is used as a resilient high-abrasion topcoat for traffic-bearing waterproofing systems in high demand areas such as turning lanes, ramps and booth entrance areas. It can be recoated for additional wear resistance. Anti-slip performance is achieved by broadcasting silica sand or aluminum oxide grit into the coating.
- Ideal For**
- Parking decks
 - High traffic areas – ramps, turning lanes and booth-collection areas
 - Mechanical rooms with extreme traffic
 - Plaza, pool and recreational decks, and vehicular ramps
 - Stadiums
- Features**
- Resilient coating with high abrasion resistance
 - Outstanding water-impermeability sealing properties
 - Very low odour and zero VOCs
 - Potential LEED credits
 - Excellent water immersion properties
 - Self-cleaning, fast curing, and easy to apply and to maintain
 - Superior abrasion and scratch resistance; high tensile strength

TECHNICAL DATA

PHYSICAL PROPERTIES		
Colour	Please see <i>Durex® Colour Selection Guide</i> for available colour options.	
Resin Type	Polyurethane	
Mix Ratio	Part A (Resin) : Part B (Urethane) 3:1 by volume	
Cure Time @ 35-40°C	To touch: 4 hours To recoat: 6-8 hours	
Pot Life @ 23°C	25 minutes	
Coverage	89 ft ² /gal @ 18 mils DFT	
Recommended Film Thickness	15-25 mils DFT	
Recycled Content	53%	
PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Percent Solids	ASTM D7232-06	100%
V.O.C.	ASTM D3960	0 g/L
Specific Gravity	ASTM D333	1.25 ± 0.05 g/L
Viscosity	ASTM D2196	2500 cps
Abrasion Resistance	ASTM D5178-91, CS-17 wheel	11 mg loss, 1000 g load, 1000 cycles
Tensile Strength	ASTM D412	2,800 psi
Tear Strength	ASTM D624	171 lb-lin.inch (30 KN/ lin. metre)
Elongation	ASTM D412	30%
Flexural Modulus	ASTM D522	2 mm film passes 12 mm mandrel
Low Temperature Flexibility	1/8" Mandrel @ -26°C	Pass
Water Absorption	ASTM D570	< 0.5%
Water Vapour Transmission	ASTM E96	0.29 metric perm
Shore Hardness	D	75
Chemical Resistance	ASTM D543	30% NaOH = 0.40% 10% H ₂ SO ₄ = 0.45% 30% NaCl = 0.20% Diesel Fuel = 5.0%

Packaging	Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat is packaged in 75.6 L (20 gal), 18.9 L (5 gal) and 3.78 L (1 gal) kits, as well as bulk kits. This product is available in multiple standard colours. Custom colour matching can also be attained at an additional cost. Please refer to the <i>Durex® Colour Selection Guide</i> for all available colour options.
Storage Conditions	Store Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. KEEP FROM FREEZING.
Surface Preparation	Maintain temperature in work areas to receive floor coating at a minimum of 10 degrees C for at least 24 hours before application, during application, and until coatings have fully cured. Substrate must be at least 10 degrees C and 3 degrees C above dew point prior to application. Provide adequate ventilation where flooring is being applied. Maintain a dust-free environment for duration of work. Erect suitable barriers to prevent through traffic or other trades from entering working area during installation of floor coating and to protect adjacent surfaces from damage. Allow 8 hours for Durex® Uraflex 360 Elastomeric Polyurethane Waterproofing Membrane to dry, immediately followed by the application of Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat to allow the two materials to react. Durex® Uraflex 360 Elastomeric Polyurethane Waterproofing Membrane to be coated with 24 hours of application.
Mixing Instructions	Mixing shall be carried out in a clean, rust-free container, and mixed by a power drill at 400-500 rpm maximum. Do not mix Part A and Part B together until ready for application, only mix materials to be used within working time window. Mix the kit as provided in full (3 parts by volume of Part 'A' resin with 1 part by volume of Part 'B' urethane). Mix Part A and Part B together slowly using a low-speed drill for a minimum of 5 minutes, ensuring that both components are thoroughly mixed and there is a consistent colour without any residue remaining on the sides of the pail. Extra care must be taken to avoid introducing air into the mixture.
Application	Apply Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat at a uniform thickness of 15-25 wet mils using a 13 mm phenolic core roller or notched squeegee over Durex® Uraflex 360 and/or Durex® Uraflex 361. Refer to Durex® Uraflex Traffic-Bearing Waterproofing System data sheet for system installation instructions. Use wet film thickness gauge to measure and monitor material thickness. Anti-Slip Surfaces: Broadcast a #24 mesh silica sand or aluminum oxide aggregate evenly over the surface at a rate of approximately 2-5 lb per 100 sq. within 5-10 minutes of application. Allow the sand/coating matrix to settle, self-level and encapsulate the aggregate into the coating, immediately followed by back-rolling the aggregate for a smooth, consistent finish. Extreme Traffic Areas: Apply an additional coat of Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat for extreme traffic areas. Apply coatings between 8-16 hours of each application. Coatings cured longer than 16 hours must be mechanically abraded and primed prior to additional applications. Contact Durabond Technical Services for information when specifying heavy-duty traffic applications.
Clean-up	Wash all tools and equipment immediately with mineral Xylene or solvent-based cleaner. Allow any unused product to harden in container and discard according to local regulations.
Limitations	Do not use Durex® Uraflex 362 Elastomeric Polyurethane Traffic-Bearing Topcoat if temperature is less than 5 degrees C. Topcoat with Durex® Uraflex 375 UV Non-Yellowing Elastomeric Polyurethane Traffic-Bearing Topcoat for exterior or UV-exposed applications. Always adhere to published recoating schedules to ensure coating adhesion.
Health and Safety	Use under well-ventilated conditions with appropriate respirator approved for organic vapours and rubber gloves when handling the product. Full eye and skin protection are required when using this product. Harmful if swallowed. Keep product out of reach of children. Read published Safety Data Sheet prior to use.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd. sales representative.

DURabond

Technical Coatings Ltd

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01