

# Durex® Acrotel Sport Court Basecoat

## Flexible Waterproofing Primer for Acrotel Sports Court System

<b>Description</b>	Durex® Acrotel Sport Court Basecoat is a single component, waterborne acrylic copolymer high build waterproofing coating that functions as a basecoat for sport court applications.
<b>Uses</b>	Durex® Acrotel Sport Court Basecoat is a high-performance flexible coating that will waterproof substrates and has excellent adhesion to a variety of surfaces. It will bridge hairline cracks and move with substrate throughout a wide range of temperatures from -35°C to 80°C.
<b>Ideal For</b>	<ul style="list-style-type: none"> <li>• Tennis courts</li> <li>• Bocce courts</li> <li>• Ice arenas</li> </ul>
<b>Features</b>	<ul style="list-style-type: none"> <li>• Low odour and VOCs</li> <li>• Low Tg, long lasting crack bridging in low and high temperatures</li> <li>• Penetrates and adheres to concrete and masonry substrates</li> <li>• Outstanding water ponding properties, with no water penetration</li> <li>• Excellent mildew and alkaline resistance</li> <li>• Waterborne, simple, clean and safe to handle</li> <li>• Non-flammable</li> </ul>

### TECHNICAL DATA

#### PHYSICAL PROPERTIES

<b>Colour</b>	Pigmentable
<b>Resin Type</b>	Acrylic copolymer
<b>Coverage</b>	200 ft <sup>2</sup> /gal @ 10 mils WFT (5 mils DFT)
<b>Drying Time @ 23°C (75°F), 55% RH</b>	To touch/recoat: 1 hour Full cure: 7 days
<b>Min. Film Forming Temperature</b>	10°C
<b>pH Level</b>	8.5 – 9.5
<b>Reducer/Clean Up</b>	Water

#### PERFORMANCE PROPERTIES

PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
<b>Percent Solids</b>	ASTM D 7232-06	45-50% (vol.)/50-55% (wt.)
<b>Specific Gravity</b>	ASTM D 333	1.20 ± 0.10 g/L 10.50 ± 0.30 lb/gal
<b>Water Vapour Transmission</b>	ASTM D 6763-08	8.0 lb/in.
<b>Tensile Strength</b>	ASTM D 2370	140 psi @ 24°C/75°F
<b>Elongation</b>	ASTM D 2370	150% @ 18°C/0°F 350% @ 0°C/32°F 700% @ 24°C/75°F
<b>Viscosity (Brookfield) 23°C (75°F)</b>	ASTM D 2196	1000-4000 cps
<b>Flexibility (Mandrel Bend)</b>	ASTM D 522	1/2" Mandrel @ -34°C/-30°F 1/8" Mandrel @ -26°C/-15°F

<b>Packaging</b>	Durex® Acrotel Sport Court Basecoat is packaged in 18.9 L (5 gal) and 3.78 L (1 gal) kits.
<b>Storage Conditions</b>	Durex® Acrotel Sport Court Basecoat in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. KEEP FROM FREEZING.
<b>Surface Preparation</b>	Clean surfaces with a wire brush and/or power washer to remove dirt, loose materials and debris, and/or other materials deleterious to adhesion. Allow surfaces to thoroughly dry prior to applications. Fill cracks and holes, and retool mortar joints to provide a smooth uniform surface. Clean and remove paint back to the original surface. New concrete and masonry mortar should be allowed to cure for a minimum of 30 days. If the surface has been previously painted, the coating must be stripped and completely removed. Mechanical abrasion is recommended.
<b>Application</b>	Prepare a test patch to verify the effectiveness of the cleaning process, and to check product adhesion to the surface. Do not proceed with applications prior to, during, or after inclement weather conditions, or if adverse weather is anticipated within 24 hours after application. Use a good quality synthetic brush, roller or airless sprayer to apply an even coat of Durex® Acrotel Sport Court Basecoat. Maintain a wet edge to prevent overlap marks and gloss differences. Durex® Acrotel Sport Court Basecoat is designed to be applied in a two-part system as a primer/basecoat before applying Durex® Acrotel Sport Court Topcoat.
<b>Health and Safety</b>	Take suitable fire precautions. Use under well ventilated conditions with appropriate respirator approved for organic vapours and rubber gloves when handling the product. Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water and seek medical attention if irritation occurs. Harmful if swallowed. Do not induce vomiting. Drink 1-2 glass of water or milk. Keep product out of reach of children. Read published Material Safety Data Sheet for additional information.
<b>Warranty</b>	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
<b>Technical Services</b>	Technical support is available upon request at <a href="mailto:info@durabond.com">info@durabond.com</a> . For the latest version of this data sheet, please visit our website at <a href="http://www.durabond.com">www.durabond.com</a> , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd sales representative.

# DURabond

Technical Coatings Ltd

**HEAD OFFICE**  
55 Underwriters Road  
Scarborough, ON M1R 3B4  
T 416.759.4474 F 416.759.4470

**MISSISSAUGA**  
6178 Netherhart Road  
Mississauga, ON L5T 1B7  
T 905.565.9283 F 905.565.9365

**EDMONTON**  
14345 120<sup>th</sup> Avenue  
Edmonton, AB T5L 2R8  
T 780.451.6364 F 780.453.9056

[INFO@DURABOND.COM](mailto:INFO@DURABOND.COM)

[WWW.DURABOND.COM](http://WWW.DURABOND.COM)

1.877.DURABOND (387.2266)

V2.01