

Durex® Cement Finish Blend

Cement / Sand Mixture for Concrete Patching and Repairing

Description	Durex® Cement Finish Blend is a cement/sand mix that incorporates a well-balanced blend of selected aggregates and fillers formulated to provide ideal physical properties and excellent workability features for the patching and repair of concrete floors and walls.
Uses	Durex® Cement Finish Blend is a versatile product which can be used in the patching and repair of concrete floors and walls. It is to be installed as a repair material prior to a self-leveling underlayment topping and/or any other decorative flooring overlays and as a repair mortar compound for repairing and smoothing concrete walls and overhead repairs. Durex® Cement Finish Blend can be used as a concrete repair for Durex® Protective Floor Coatings.
Advantages	<p>Durex® Cement Finish Blend has been formulated with numerous ideal features to facilitate and simplify its application:</p> <ul style="list-style-type: none"> • Bagged, ready to use by simply mixing with Durex® Acrylic Resin Bond or Durex® Acrybond Concentrate additive • Excellent workability • Low shrinkage, thus resulting in minimum cracking • Excellent compressive and flexural strength • Versatility - one product suitable for many applications • Excellent adhesion to most common surfaces • Excellent freeze-thaw stability
Limitations	<ul style="list-style-type: none"> • Ambient, surface and material temperatures must be above 5°C (41°F) during application and curing period • Allow to cure for 24 hours before topping with a self-leveling underlayment. • Allow to cure for 7+ days before topping with a non-permeable protective coating and epoxy/polyurethane coatings. All patches must be measured to be below 4% moisture content.

TECHNICAL DATA

PHYSICAL PROPERTIES	
Appearance	Grey cementitious sand mix
Toxicity	CAS Registry No. 65997-15-1 (contains Portland Cement)
Density	1355 kg/m ³
Bulk pot life	1 hr to 2 hrs (depending on ambient conditions and type of polymer used)

PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Compressive Strength	ASTM C109	44.8 MPa (6560 psi)
Flexural Strength	ASTM C348	6.55 MPa (948 psi)
Shear Bond Adhesion	ASTM C1042	10.6 MPa (1540 psi)
Tensile Strength	ASTM C190	6.00 MPa (825 psi)
Taber abrasion	ASTM C190	6.00 MPa (825 psi)

Packaging	Durex® Cement Finish Blend is packaged in 25 kg (55 lb) bags.
Storage	Store Durex® Cement Finish Blend in a dry, vented, waterproof location, stacked off the ground with ambient temperatures above 5°C (41°F). Keep materials dry, protected from rapid temperature changes, dampness and moisture and away from direct sunlight. KEEP FROM FREEZING.
Coverage	One bag of Durex® Cement Finish Blend mixed with 4-5 litres (140 – 176 oz) of Acrylic Resin Bond covers approximately 2.5 m ² (27 ft ²) at a thickness of 6.3 mm (1/4”).
Surface Preparation	Substrate must be dry, solid, clean and sound, free of weak and powdery surfaces, dust, dirt, oil, grease and other deleterious materials detrimental to a positive bond.

Mixing Procedure

Mix Durex[®] Cement Finish Blend with in accordance with the following formula:

Major Concrete Repairs & Moisture Subjected Areas:

- 1 bag, 25 Kg (55 lbs) Durex[®] Cement Blend Mix
 - 4-5 litres (140 – 176 oz) Durex[®] Acrylic Resin Bond
- Or Alternatively:
- 1 bag, 25 Kg (55 lbs) Durex[®] Cement Blend Mix
 - 2-2.5 litres (70 – 88 oz) Durex[®] Acrybond Concentrate
 - 2-2.5 litres (70 – 88 oz) Potable Water

Surface Area Patching & Overhead Repairs:

- 1 bag, 25 Kg (55 lbs) Durex[®] Cement Blend Mix
 - 2 litres (70 oz) Durex[®] Acrylic Resin Bond
 - 2 – 2.5 litres (70 – 88 oz) Potable Water
- Or Alternatively:
- 1 bag, 25 Kg (55 lbs) Durex[®] Cement Blend Mix
 - 1 litre (35 oz) Durex[®] Acrybond Concentrate
 - 3 - 3.5 litres (105 - 125 oz) Potable Water

Interior Wall Parging & Patching / Non-Moisture Subjected Areas:

- 1 bag, 25 Kg (55 lbs) Durex[®] Cement Blend Mix
- 1/2 litre (17.5 ounces) Durex[®] Cement Bond
- 3.5 – 4 litres (approx. 1 gallon) Potable Water

Pour the water into a clean empty mixing container. While under slow mixing action add the Durex[®] Cement Blend Mix in the required mixing proportions. Mix well until the mixture is free of lumps. Do not over-mix or use excessive mixing speed. Let mixed material stand for a few minutes until they begin initial stiffening. Mix only enough material which can be used within 45 minutes. Re-temper and use. Discard all materials which have begun to stiffen for a second time. **DO NOT SUBSTITUTE NOR COMPENSATE WITH OTHER ADDITIVES.**

Application

Durex[®] Cement Finish Blend is to be applied by metal trowel and smooth/finish as required. Durex[®] Cement Finish Blend can be installed to a maximum thickness of ½” (12mm) per application. Applications over ½” (12mm) can be installed in multiple coats, or through the addition of pea gravel (maximum 10mm in diameter) into the mixture at a rate of 5-7kg per bag.

Clean-up

Clean all tools promptly after each use with clean water. Do not allow mixes to dry on tools.

Health and Safety

For information and advice on the safe handling, storage and disposal of chemical products, refer to the most recent MSDS sheet containing physical, environmental, toxic and other safety/materials handling data. For industrial use only. Keep out of reach of children.

Warranty

Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.

Technical Services

Technical support is available upon request at info@durabond.com. For the latest version of this data sheet, please visit our website at www.durabond.com, call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Products Ltd. sales representative.

DURabond

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V3.01