

Durex Acrotel CP

Exterior Concrete & Masonry Protective Coating

- Description** Durex® Acrotel CP Exterior Concrete & Masonry Protective Coating is an extremely durable, VOC-compliant solvent-based, reinforced liquid-applied cementitious coating. It features ionic bonding technology for excellent adhesion to concrete and masonry substrates for a wide variety of protective applications.
- Uses** Durex® Acrotel CP Exterior Concrete & Masonry Protective Coating is used on exterior concrete and masonry surfaces for a long-lasting, protective finish suitable for applications in harsh environments. Durex® Acrotel CP Exterior Concrete & Masonry Protective Coating can be used as a primer coating in exterior and interior applications as well as light-traffic floor areas.
- Ideal For**
- Exterior coating for concrete and masonry buildings
 - Protecting reinforced concrete & concrete structures
 - Balconies & light-traffic concrete floors
- Features**
- Low odour and VOC-compliant breathable coating
 - Efflorescence resistant
 - Water, mildew and alkaline resistant
 - Resistance to saponification caused by alkaline substrates
 - Matte finish, available in smooth or light grit texture
 - Application to green concrete
 - Ionic Bond Technology with excellent adhesion to concrete and masonry substrates
 - Excellent exterior durability and self-cleaning properties
 - Cures down to -5°C; available in winter grade for low temperature applications (down to -20°C)

TECHNICAL DATA

PHYSICAL PROPERTIES		
Finish	Smooth or Light Sand Texture	
Colour	Please see <i>Durex® Colour Selection Guide</i> for available colour options.	
Resin Type	Acrylic copolymer	
Coverage	3-5 m ² /L (150-200 ft ² /gal) @ 3-5 mils DFT	
Cure Time @ 23°C (75°F), 55% RH	To touch: 1 hour To recoat: 4 hours Fully cured: 7 days	
Sheen	Flat	
Reducer/Clean-up	Special solvent or mineral spirit	
PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Percent Solids	ASTM D7232-06	45 ± 5% (vol.)
Viscosity (Brookfield) 23°C (75°F)	ASTM D2196	2,000-3,000 cps
V.O.C.	ASTM D3960-05	250 g/L
Specific Gravity	ASTM D333	1.3 ± 0.05 g/L 11.00 ± 0.1 lb/gal
WVP (Water Vapour Permeance)	ASTM D1653-13	English Perm 35/ng/(m ² .Pa.s): 2010
Flash Point Closed Cup		40°C (140°F)

Packaging	Durex® Acrotel CP Exterior Concrete & Masonry Protective Coating is packaged in 18.9 L (5 gal) and 3.78 L (1 gal) pails. This product is available in multiple standard colours. Custom colour matching can also be attained at an additional cost. Please refer to the <i>Durex® Colour Selection Guide</i> for all available colour options.
Storage Conditions	Store Durex® Acrotel CP Exterior Concrete & Masonry Protective Coating in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store liquid materials in ambient temperatures above 5 degrees C and below 35 degrees C. KEEP FROM FREEZING.
Surface Preparation	Clean surfaces with a wire brush and/or power washer to remove dirt, loose materials and debris, and/or other materials deleterious to adhesion. Allow surfaces to thoroughly dry prior to applications. Fill cracks and holes, and retool mortar joints to provide a smooth uniform surface. Provide a perimeter drip edge for horizontal applications to minimize the visual effects of surface runoff. Do not use in locations subject to continuous water immersion.
Application	<p>THOROUGHLY MIX PRIOR TO USE. DO NOT DILUTE WITH WATER OR OTHER ADDITIVES.</p> <p>Prepare a test patch to verify the effectiveness of the cleaning process, and to check product adhesion to the surface. Do not proceed with applications prior to, during, or after inclement weather conditions, or if adverse weather is anticipated within 24 hours after application. Apply materials at ambient temperatures above -5 degrees C. For cold temperature applications ensure that the surface is ice and frost free. Use Acrotel CP Winter Grade in applications below -5 degrees C. Lower temperatures will lengthen cure times. Durex® Acrotel CP can be applied using rollers, power sprayers or brushes. Rollers should be lint free and solvent resistant, having a nap of 19 mm to 31 mm (3/4 to 1 1/4 inch) in order to achieve the coverage rate. Provide a perimeter drip edge for horizontal applications to minimize the visual effects of surface runoff. Do not use in locations subject to continuous water immersion.</p>
Clean Up	Wash all tools and equipment immediately after use with mineral spirits.
Maintenance	None required.
Limitations	When applying in sub-zero temperatures, surface must be free of ice, snow and frost.
Health and Safety	Take suitable fire precautions. Use under well-ventilated conditions with appropriate respirator approved for organic vapours and rubber gloves when handling the product. Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water and seek medical attention if irritation occurs. Harmful if swallowed. Do not induce vomiting. Drink 1-2 glasses of water or milk. Keep product out of reach of children. Read published Material Safety Data Sheet for additional information.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd sales representative.

DURabond

Technical Coatings Ltd

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01