

Durex® Acrotel Procover

High-Performance Latex Paint

Description	Durex® Acrotel Procover High-Performance Latex Paint is a single-component, environmentally friendly, low-VOC, water-based acrylic paint for exterior and interior use. It is specially formulated to be used as a premium quality paint over gypsum wall board, cement board, poured concrete, masonry, stucco, EIFS and a variety of other services.
Uses	Durex® Acrotel Procover High-Performance Latex Paint is a high-quality multi-use exterior and interior latex paint ideal for coating a variety of surfaces such as gypsum wall board, cement board, poured concrete, masonry, stucco, EIFS and many other applications. It is also used as a primer for any of our Durex Architectural Coatings and our Durex Protective Coatings.
Ideal For	<ul style="list-style-type: none"> Interior and exterior surfaces such as walls, ceilings and columns Residential, industrial, institutional and commercial interior walls Excellent for recoating existing stucco and EIFS Perfect for coating exterior concrete balcony soffits, poured concrete and brick surfaces New or existing construction applications
Advantages	<ul style="list-style-type: none"> Superior hiding power Waterborne, simple, clean and safe to handle Low odour and VOC compliant Excellent water and alkaline resistance Economical, high surface coverage Flexible finish, stands up to peeling and cracking Advanced anti-fade formula Mold, mildew and algae resistant coating Excellent leveling, flow and microform-free properties Excellent adhesion to variety of substrates Non-flammable

TECHNICAL DATA

PHYSICAL PROPERTIES		
Colour	Please see <i>Durex® Colour Selection Guide</i> for available colour options.	
Resin Type	Acrylic	
Coverage	7.4 – 9.8 m ² /L (300 – 400 ft ² /gal) @ 4 – 5 mils WFT	
Cure Time @ 23°C (75°F), 55% RH	To touch: 1 hour To recoat: 2 hours	
pH Level	8.0 – 9.0	
Reducer/Clean-up	Water	
PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Percent Solids	ASTM D7232-06	50 ± 2% (vol.)
Viscosity (Brookfield) 23°C (75°F)	ASTM D2196	80-100 KU @ 23°C (75°F)
V.O.C. (Without Water)	ASTM D3960-05	30 g/L 0.24 lb/gal
Specific Gravity	ASTM D333	1.55 ± 0.05 g/L 12.80 ± 0.1 lb/gal
Sheen (60°)		Low-mid sheen

Packaging	Durex® Acrotel Procover High-Performance Interior Latex Paint is packaged in 18.9 L (5 gal) and 3.78 L (1 gal) pails. This product is available in multiple standard colours. Custom colour matching can also be attained at an additional cost. Please refer to the <i>Durex® Colour Selection Guide</i> for all available colour options.
Storage Conditions	Store Durex® Acrotel Procover High-Performance Interior Latex Paint in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store liquid materials in ambient temperatures above 5 degrees C and below 35 degrees C. KEEP FROM FREEZING.
Surface Preparation	Clean surfaces with a wire brush and/or power washer to remove dirt, loose materials and debris, and/or other materials deleterious to adhesion. Allow surfaces to thoroughly dry prior to applications. Fill cracks and holes, and retool mortar joints to provide a smooth uniform surface. If wall has been sealed with sealer, remove it by power washing with detergent. If surface has been sealed with sealer, remove it by power washing with detergent. If the wall has been previously painted, cut the old paint with an X-shape and tape it down firmly using duct tape. Pull firmly on the tape to remove. If 25% or more of the paint is removed with the tape, the painted surface is not bonded properly. Remove old paint by power washing or shot blast. If less than 25% of the paint is removed, proceed to next step of application.
Application	<p>THOROUGHLY MIX PRIOR TO USE. DO NOT DILUTE WITH WATER OR OTHER ADDITIVES.</p> <p>Prepare a test patch to verify the effectiveness of the cleaning process, and to check product adhesion to the surface. Do not proceed with applications prior to, during, or after inclement weather conditions, or if adverse weather is anticipated within 24 hours after application. Apply materials at ambient temperatures above 5 degrees C. Using a good quality synthetic brush, roller or airless spray, apply an even coat of Durex® Acrotel Procover High-Performance Interior Latex Paint.</p> <p>Note: Film formation of Durex® Acrotel Procover High-Performance Interior Latex Paint depends on temperature and humidity. Minimum film formation temperature is 5°C (40°F) and maximum relative humidity is 60%. As a rule, lower temperature and higher humidity will result in longer curing time.</p>
Clean-Up	Wash all tools and equipment immediately after use with water and mild detergent.
Health and Safety	Take suitable fire precautions. Use under well-ventilated conditions with appropriate respirator approved for organic vapours and rubber gloves when handling the product. Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water and seek medical attention if irritation occurs. Harmful if swallowed. Do not induce vomiting. Drink 1-2 glasses of water or milk. Keep product out of reach of children. Read published Material Safety Data Sheet for additional information.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd sales representative.

DURabond

Technical Coatings Ltd

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01