

# Durex® Dur-A-Hard Quartz Broadcast

Decorative, High-Build, Multi-Layered, Broadcasted, Self-Leveling, Cementitious, Polyurethane Flooring System

<b>Description</b>	Durex® Dur-A-Hard Quartz Broadcast is a pourable, phthalate & solvent-free, cementitious polyurethane floor system designed to provide a decorative yet high build, tough and durable, non-slip textured surface for wet and dry production areas predominately in the food and beverage industry. It consists of a layer of Dur-A-Hard Quartz Broadcast which is then broadcasted to refusal with coloured quartz aggregates for additional strength. It is then top coated with Durex® Polyuretel to seal in the broadcasted aggregates at to give additional surface performance.
<b>Uses</b>	Durex® Dur-A-Hard Quartz Broadcast is a broadcasted to refusal, odourless, 1/4" self-leveling flooring system approved for use in the food and beverage industry for heavy duty areas. Durex® Dur-A-Hard Quartz Broadcast is designed as a decorative flooring system that is capable of protecting concrete floor surfaces against organic and inorganic chemical compounds and bacterial growth, and withstands thermal shock under extreme cold and heat steam treatments. It is designed to be installed for high demand flooring areas.
<b>Ideal For</b>	<ul style="list-style-type: none"> <li>• Pharmaceutical laboratories and clean rooms</li> <li>• Chemical processing plants and containment storage rooms</li> <li>• Production processes exposed to aggressive chemicals</li> <li>• Commercial and restaurant kitchens</li> <li>• Wet areas, loading docks, garbage rooms and high impact areas</li> </ul>
<b>Features</b>	<ul style="list-style-type: none"> <li>• CFIA approved; USDA accepted</li> <li>• Zero VOCs, odorless, and non-tainting</li> <li>• Anti-microbial and resistant to organic and inorganic chemical compounds and bacterial growth</li> <li>• Chemical and abrasion resistant</li> <li>• Thermal shock resistant and Wide Service Temperature Range (-20°C to 120°C)</li> <li>• Easy to apply, easy to clean and sterilize</li> <li>• May be applied at low temperatures (5°C)</li> <li>• Seamless waterproof slip-resistant floor topping</li> <li>• Will bond to mild steel and water-resistant plywood.</li> </ul>

## TECHNICAL DATA

PHYSICAL PROPERTIES		
<b>Colour</b>	Please see <i>Durex® Colour Selection Guide</i> for available colour options.	
<b>Adhesion to Concrete</b>	>400 psi (concrete fails before loss of bond)	
<b>Cure Time @ 21°C</b>	Foot Traffic: 12-14 hours Light Traffic: 24-36 hours Full Service: 48 hours Full Cure: 240 hours	
<b>Mix Ratio (by volume)</b>	<i>Full Kit as Supplied</i>	
<b>Coverage (per kit)</b>	2.1 m <sup>2</sup> @ 4.5 mm (25 ft <sup>2</sup> @ 5/16 in) / 1.4 m <sup>2</sup> @ 6 mm (19 ft <sup>2</sup> @ ¼ in)	
<b>Pot Life – working time @ 21°C</b>	20 minutes <b>Note:</b> Pot life is shorter at higher temperatures. Do not use below 5°C or above 30°C.	
<b>Service Temperature</b>	-20°C to 120°C (steam wash)	
PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
<b>Abrasion Resistance</b> CS17 Wheel 1000 GM Load 1000 Cycles	ASTM C501	35 mg loss
<b>Coefficient of Friction</b> Standard Slip-Resistant	ASTM D2047	0.9
<b>Compressive Strength</b>	ASTM C579	56 MPa (8,200 psi)
<b>Flexural Strength</b>	ASTM C580	20 MPa (2,908 psi)
<b>Impact Resistance @ 125 mils</b>	MIL D3134	Pass
<b>Tensile Strength</b>	ASTM C307	9.3 MPa (1,400 psi)

<b>Packaging</b>	Durex® Dur-A-Hard Quartz Broadcast Self-Leveling Broadcasted Cementitious Polyurethane Flooring System is packed as a 4-component kit based on mixing ratios; Part A (2.5Kg), Part B (2.5Kg), Part D colorant and Part C in 16 kg bag mix is a cementitious admixture. This product is available in limited standard colours. Custom colour matching can also be attained at an additional cost. Please refer to the <i>Durex® Colour Selection Guide</i> for all available colour options.
<b>Storage Conditions</b>	Store Durex® Dur-A-Hard Quartz Broadcast Self-Leveling Broadcasted Cementitious Polyurethane Flooring System in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store liquid materials in ambient temperatures above 10 degrees C and below 25 degrees C. <b>KEEP FROM FREEZING.</b> Durex® Dur-A-Hard SL has a shelf life of 6 months.
<b>Surface Preparation</b>	Surfaces to be coated must be prepared to ICRI CSP 3, be clean, dry, structurally sound and free of oils and debris or other materials deleterious to adhesion. Deficiencies in the substrate to be repaired as required, please consult Durabond. Primer may be required depending on the substrate porosity and contamination. Consult Durabond.
<b>Edge Termination</b>	All the free edges of Durex® Dur-A-Hard floor whether at the perimeter, along gutter or at drains require extra anchorages to distribute mechanical and thermal stresses. This is best achieved by forming or cutting grooves in the concrete. Grooves should have a depth and width of two times thickness of the Durex® Dur-A-Hard flooring material.
<b>Moisture Concerns</b>	Moisture content in the slab is to be measured prior to application of flooring system to prevent craters and blistering, due to out-gassing of repaired or freshly prepared substrates.
<b>Mixing Equipment</b>	Mixing shall be carried out with a clean, rust-free paddle mixer that shall minimize air entrainment, powered by a power drill at 400-500 rpm maximum.
<b>Mixing Instructions</b>	Durex® Dur-A-Hard Quartz Broadcast Self-Leveling Broadcasted Cementitious Polyurethane Flooring System is supplied in a kit based on mix ratio. Combine Part A, Part D and Part B liquid components in a clean plastic container and mix for two minutes. Combine the liquid mixture component with the dry Part C component in a separate large container (20 L pail) and mix for two minutes. Durex® Dur-A-Hard Quartz Broadcast must be applied immediately for best working time and results. Please refer to chosen top coat TDS sheet for mixing instructions.
<b>Application Method</b>	Apply the mixed product onto prepared floor and spread using pin rake and/or squeegee. Substrate and ambient temperature must be between 4 degrees C and 25 degrees C during application and curing. Spread the material onto the floor at an average wet film thickness of 4.5 mm to 6mm. Immediately Spike Roll to release entrapped air. Broadcast 20-30 mesh silica sand aggregate (or as chosen) into wet coating to refusal. Once cured, vacuum excess silica sand. Apply Durex® topcoat (Durex® Dur-A-Hard Topcoat, Durex® Uraflex 100 or recommended topcoat) at a thickness of 10 mils DFT or as required.
<b>Cleaning</b>	Regular cleaning will maintain these systems in serviceable condition. However, certain textures and service environments require specific procedures. Contact Durabond Technical Services for further information and recommendations.
<b>Health and Safety</b>	Read respective SDS Sheets prior to handling, storage and usage of materials. Refer to SDS sheets for all health and safety information. Protective clothing and eyewear must be used at all times. Keep out of reach of Children.
<b>Warranty</b>	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
<b>Technical Services</b>	Technical support is available upon request at <a href="mailto:info@durabond.com">info@durabond.com</a> . For the latest version of this data sheet, please visit our website at <a href="http://www.durabond.com">www.durabond.com</a> , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd. sales representative.



Technical Coatings Ltd

**HEAD OFFICE**  
55 Underwriters Road  
Scarborough, ON M1R 3B4  
T 416.759.4474 F 416.759.4470

**MISSISSAUGA**  
6178 Netherhart Road  
Mississauga, ON L5T 1B7  
T 905.565.9283 F 905.565.9365

**EDMONTON**  
14345 120<sup>th</sup> Avenue  
Edmonton, AB T5L 2R8  
T 780.451.6364 F 780.453.9056

[INFO@DURABOND.COM](mailto:INFO@DURABOND.COM)

[WWW.DURABOND.COM](http://WWW.DURABOND.COM)

1.877.DURABOND (387.2266)

V2.01